

Mirafi® RSi - Series Woven Geosynthetics

The Mirafi® RSi Series is a revolutionary geotextile created from super high-tenacity polypropylene filaments formed into an innovative weave to provide superior reinforcement strength and soil interaction integrated with high water flow and soil retention capabilities. It is extremely robust and suitable for laying directly over soft subgrade with minimum manpower.

Properties of Mirafi® RSi - Series Woven Geosynthetics

Property		Test Method	Unit	RS 380i	RS 580i
Mechanical					
Characteristic Tensile Strength at 2% Strain	CD	ASTM D4595	kN/m	20	26
Characteristic Tensile Strength at 2% Strain	MD	ASTM D4595	kN/m	8	9
CBR Puncture Strength		ASTM D6241	N	6600	9000
Grab Strength		ASTM D4632	N	1500	2100
Trapezoidal Tear Strength		ASTM D4533	N	600	700
G-Rating		Austroroads	-	7000 ¹	10000 ¹
Hydraulic					
Flow Rate		ASTM D4491	l/min/m ²	3050	3050
Permittivity		ASTM D4491	sec ⁻¹	0.9	1.0
Soil Retention					
Apparent Opening Size, O ₉₅		ASTM D4751	mm	0.43	0.43
Effective Opening Size, O ₉₀		ISO 12956	mm	0.35	0.30
Soil Interaction					
Interaction Coefficient (<i>Direct Shear</i>)		ASTM D5321	-	0.80 ¹	0.80 ¹
Interaction Coefficient (<i>Pull-out</i>)		ASTM D6706	-	0.89 ¹	0.90 ¹
Resistance to Installation Damage		ASTM D5818	% strength retained	90 ¹	90 ¹
UV Resistance (at 500 hours)		ASTM D4355	% strength retained	90	90
Physical Properties					
Roll Dimension (width x length)			m	4.6 x 100	4.6 x 100
Roll Area			m ²	460	460

¹ G-Rating, interaction coefficient (for sand or gravel) and resistance to installation damage (for sandy gravel) values are based on tests conducted by external test laboratories.

TenCate Mirafi® is a registered trademark of Royal Ten Cate.

Disclaimer :

TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all expressed, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Further details of this application and products can be obtained by contacting your nearest TenCate Technical Support office. Unauthorized reproduction and distribution prohibited.