

# AUSTRALIAN-MADE TO STABILISE COASTAL STRUCTURES AND PROTECT LANDFILL

## TEXCEL® R NON-WOVEN STABLE FIBRE GEOTEXTILE

### TECHNICAL DATA SHEET: TYPICAL VALUES

Texcel R is non-woven staple fibre geotextile developed to stabilise coastal structures and protect landfill lining systems. Made using either polyester and/or polypropylene fibres, they have a unique staple fibre blend and an inbuilt flexibility to allow engineers to specify mechanical and hydraulic criteria to suit tough environmental conditions.

- Significantly reduces force placed on impermeable liners, protecting them in the short and long term
- High abrasion, UV resistance and consistent mechanical and hydraulic performance
- Made in Australia, developed and tested in accordance with Australian standards
- High elongation properties minimising installation damage and ensuring effective soil contact, interaction and stability
- Applicable for Road, Water, Coastal and Waste sectors



### TEXCEL R - TYPICAL VALUES TECHNICAL DATA

TEST	UNITS	400R	600R	900R	1200R
Fibre Type	-	100% Virgin Polyester Fibre			
CBR Burst Strength (AS 3706.4)	N	2,750	4,360	6,140	8,850
CBR Toughness (AS 3706.4)	kJ/m <sup>2</sup>	2.7	5.6	8.1	9.3
Wide Strip Tensile Strength MD <sup>1</sup> (AS 3706.2)	kN/m	14.8	21.2	30.4	45.5
Wide Strip Tensile Strength XMD <sup>2</sup> (AS 3706.2)	kN/m	15.6	26.6	38.9	57.2
Wide Strip Toughness MD (AS 3706.2)	kJ/m <sup>2</sup>	5.5	10.2	14.6	21.7
Wide Strip Toughness XMD (AS 3706.2)	kJ/m <sup>2</sup>	5.8	12.7	18.6	30.0
Grab Tensile Strength MD (AS 3706.2)	N	820	1,250	1,790	2,800
Grab Tensile Strength XMD (AS 3706.2)	N	870	1,440	2,160	3,260
Abrasion Resistance MD/XMD (BAW Rotating Drum)	kN/m Strength Retained	7.5/6.9	17.3/17.3	22.7/26.2	34.2/40.5
12 Month Outdoor Exposure MD/XMD (ASTM D5970)	kN/m Strength Retained	8.1/7.1	17.7/17.0	23.2/23.2	42.4/47.6
Hydrocarbon (Diesel) Resistance MD/XMD (AS 3706.12)	% Strength Retained	>90	>90	>90	>90
Accelerated UV Resistance MD/XMD (AS 3706.11)	% Strength Retained	>50	>60	>80	>80
Pore Size O <sub>95</sub> (AS 3706.7)	µm	≤75	≤75	≤75	≤75
Pore Size O <sub>95</sub> - Capillary Flow Method (ASTM D6767)	µm	182	124	126	108
Permittivity (AS 3706.9)	s <sup>-1</sup>	1.41	0.69	0.45	0.30
Coefficient of Permeability (AS 3706.9)	m/s x 10 <sup>-4</sup>	48	34	23	20
Flow Rate @ 100mm Head (AS 3706.9)	L/m <sup>2</sup> /s	141	69	45	30

MD=Machine direction, XMD=Cross Machine Direction

Visit [geofabrics.co](https://www.geofabrics.co) or call 1300 60 60 20 (AU)  
or [geofabrics.co.nz](https://www.geofabrics.co.nz) or call 0800 60 60 20 (NZ)

**GEOFABRICS®**  
Sustainable solutions

IMPORTANT NOTICE - DISCLAIMER - The information contained in this brochure is general in nature. In particular the content of this brochure does not take account of specific conditions that may be present at your site. For full disclaimer and further information regarding installation visit [geofabrics.co/disclaimer](https://www.geofabrics.co/disclaimer)  
© Copyright held by Geofabrics Australasia Pty Ltd. All rights are reserved and no part of this publication may be copied without prior permission. Published Sep 2021.

